



**KÖMATEX**<sup>®</sup>  
printing. lacquering. filming.

**KÖMATEX**<sup>®</sup> PVC-U plastic sheets —  
always set a good example



**Trade information for:**

- Decorators
- Advertising technicians
- Digital printers
- Design & advertising agencies
- Exhibitors
- Exhibition stand builders
- POS fitters
- Sign makers
- Modellers and prototype builders



**KÖMMERLING**<sup>®</sup>  
*Business Unit Sheets*

## **KÖMATEX® — because surface strength is always important**

**“Ideal to work with, great to finish!”**

KömaTex PVC-U sheets have a regular, fine-celled foam structure and good surface strength. The closed-cell, matt, fine-textured and high-quality surface is ideal for printing, lacquering and filming and is also easy to work. The KömaTex PVC-U sheets are also flame-resistant. All this adds up to offer ideal conditions for a highly diverse range of applications, above all in advertising.

Whether it be for signs, billboards or displays, shop-fittings or exhibition stands: KömaTex is the right choice for most purposes. Thanks to their weathering resistance, KömaTex sheets in white are also the perfect material for outdoor applications.

## **Flexible enough for a wide range of applications — strong enough for long-term use!**

KömaTex is suitable for, among other things:

### **Advertising**

For example, for signs, billboards, lettering boards, displays, shop-window displays, exhibition stands, digital direct printing, milled lettering

### **Building sector**


For example, for shopfitting, interior decorating


### **Miscellaneous**

For example, for models, photograph lamination, traffic signs for roadworks, thermoformed parts




## Top characteristics!

 .Highly suitable for bonding


 .Very suitable for printing


 .Suitable for filming

 .Easy to work


 .Flame-resistant

 .Weather-resistant

 .Very low absorption of water, no rot

 .Resistant to chemicals and corrosion

 .Thermoformable

 .Low thermal conductivity, good insulation

 .Lightweight

## Exceedingly easy to work!



### Machining

Sawing, milling, turning, cutting, punching, perforating, water-jet cutting, polishing



### Forming

Thermoforming, stretch forming, folding, bending, compression moulding, embossing, welding, bonding



### Printing, lacquering and film-laminating

Digital printing, screen printing, acrylic paints/lacquers, 2-component paints/lacquers, commercially available synthetic paints, laminating

## Standard colours



Grey 191



Red 491



Green 591



Yellow 791



Blue 891




Black 991


## Pastel colours




Apricot 446




Aqua 856



Lavender 886



Lemon 756



Mint 556



Flamingo 456

\*1 Coloured PVC-U sheets are not fully resistant to the effects of UV rays and weathering over long periods of time. They should therefore be used outdoors for limited periods only.

## Delivery programme

Sizes (mm)	White 652 thicknesses (mm)	Coloured* thicknesses (mm)	Pieces/pallet
2440 X 1220	1		200
3050 X 1220	1		200
3000 X 1000	2		140
2440 X 1220	2		140
3050 X 1220	2		140
3050 X 1560	2		140
3050 X 2050	2		90
4050 X 2050	2		60
3000 X 1000	3		125
2440 X 1220	3		125
3050 X 1220	3	X	125
3050 X 1560	3		100
3050 X 2050	3		80
4050 X 2050	3		50
3000 X 1000	4		100
2440 X 1220	4		100
3050 X 1220	4		90
3050 X 1560	4		70
3050 X 2050	4		70
4050 X 2050	4		40
2440 X 1220	5		90
3000 X 1000	5		90
3050 X 1220	5		70
3050 X 1560	5		60
3050 X 2050	5		60
4050 X 2050	5		30
2440 X 1220	6		75
3000 X 1000	6		75
3050 X 1220	6	X	60
3050 X 1560	6		50
3050 X 2050	6		50
4050 X 2050	6		25
3050 X 1560	8		50
3050 X 2050	8		30
4050 X 2050	8		20
3050 X 1220	10		50
3050 X 1560	10		40
3050 X 2050	10		30
3050 X 2050	10		20
3050 X 1220	15		30











Special lengths available on request. Protective film on one side.

# KÖMATEX® dp—always makes a great impression

Particularly in conjunction with digital printing processes, the unique surface finish of KömaTex dp combines the advantages of rapid processing and high flexibility with perfect print results. Thanks to its fine-celled, specially pretreated surface, the rigid, high-resistance PVC-U sheet is the ideal basis for true-to-detail, high-opacity and colour-fast print images. With digital direct printing in mind, our development engineers have paid special attention to ensuring the

sheets are completely flat and clean, and that they offer good adhesion for inks. The tight production tolerances also benefit printing with UV-curing or solvent-based inks, because they enable rapid processing speeds. An adhesive protection film specifically developed for KömaTex dp also ensures that the sheets are kept free of contamination before they are printed on the flat-bed printer.

## Top characteristics!

-  .Maximum possible process reliability
-  .Even tighter tolerances
-  .Surface with even better grip
-  .Good flexural strength
-  .Specially pretreated
-  .Protective film on both sides with cleaning effect
-  .Fine surface structures
-  .Tested on all flat-bed printers available
-  .Extremely good covering power
-  .Rapid processing speeds

## Delivery programme

	Sizes* in mm, White 652	Thicknesses in mm
Stock	3050 x 1220	3, 4, 5
	3050 x 1560	3, 4, 5
Quantity-based production	3050 x 1220	6, 8, 10
	3050 x 1560	6, 8, 10

\*Protective film on both sides.

## Technical Data

Properties	Test method	Unit	Thickness (mm)	Thickness (mm)
<b>Mechanical properties</b>			1-3	4-10
Apparent density*	DIN 53479/ISO 1183	g/cm <sup>3</sup>	~ 0.7	~ 0.55
Tensile stress at yield (tensile strength)	DIN 53455/ISO 527	MPa	≥ 18	≥ 12
Elongation at tear	DIN 53455/ISO 527	%	≥ 20	≥ 15
Flexural strength	DIN 53452/ISO 178	MPa	≥ 30	≥ 20
Compressive strength (range of elasticity per Hooke)	DIN 53421 (based on)	MPa	> 6	> 4
Compressive stress at 30%	DIN 53421 (based on)	MPa	> 14	> 10
Modulus of elasticity	DIN 53457/ISO 527-2/1A/50	MPa	~ 1000	~ 850
Impact strength	DIN 53453/ISO 179 (based on)	kJ/m <sup>2</sup>	~ 10	~ 10
Ball indentation hardness (49 N/30 s)	DIN 53456/ISO 2039-1	MPa	≥ 8	≥ 8
Shore hardness D	DIN 53505		~ 50	~ 50
<b>Thermal properties</b>				
Vicat softening temperature	DIN 53460/ISO 306 (process A50)	°C	≥ 75	≥ 75
Deflection temperature	DIN 53461/ISO 75 (process A50)	°C	60	60
Coefficient of linear thermal expansion from -30 °C to +50 °C	DIN 53752	mm/mK	≤ 0.08	≤ 0.08
Thermal conductivity from 0 °C to +60 °C	DIN 52612	W/mK	0.10	0.06
<b>Electrical properties</b>				
Surface resistance	DIN VDE 0303 T3/DIN IEC 93	Ω	> 10 <sup>15</sup>	> 10 <sup>15</sup>
Volume resistivity	DIN VDE 0303 T3/DIN IEC 93	Ω · m	10 <sup>14</sup>	10 <sup>14</sup>
Dielectric strength E <sub>d</sub>	DIN VDE 0303 T21	kV/mm	≥ 20	≥ 20
Comparative figure of tracking	DIN IEC 112		CTI 600	CTI 600
Dielectric constant E <sub>r</sub> (at 1 kHz)	VDE 0303 T4		~ 2.0	
Dielectric dissipation factor Tan δ (at 1 kHz)	VDE 0303 T4		~ 0.010	
<b>Other properties</b>				
Water absorption after 7 days	DIN 53495	%	< 0.3	< 0.3
Fire behaviour	DIN 4102 (D)	1-6 mm	B1	
	UL 94 (USA)	≥ 3 mm	VO	
	NFP 92-501 (F)	1-6 mm (8 + 10 mm white)	M1	M2
	Brandkennziffer (fire charac.) (CH)		5.3	
	Brandkennziffer (fire charac.) (CH)			5.3
	CSE-RF2/75 A (I) CSE-RF3/77 (I)	1-6 mm	Class 1	-
Physiological evaluation	generally recognised as safe			

\* These are standard values which apply to an average density.  
Minor variations are possible depending on the sheet thickness.